

Claims

1. Use of a first polyethylene polymer having a
5 density of at least 950 kg/m³ as a nucleating agent for a
second polyethylene polymer having a density of less
than 940 kg/m³.
2. Use of claim 1 wherein said first polyethylene
10 polymer is a homopolymer.
3. Use as claimed in claim 1 or 2 wherein the density
of the first polyethylene polymer is at least 955 kg/m³.
- 15 4. Use as claimed in claim 1 to 3 wherein the MFR₂ of
the first polyethylene polymer is 5 to 20 g/10 min.
5. Use as claimed in claim 1 to 4 wherein the amount
of first polyethylene polymer employed is 0.6 to 5 %wt,
20 relative to the weight of second polyethylene polymer.
6. Use as claimed in claim 1 to 6 wherein said second
polyethylene polymer is a copolymer or terpolymer of
ethylene with at least one C₃₋₁₀ α -olefin.
25
7. Use as claimed in claim 1 to 6 wherein said second
polyethylene polymer is made using a single site
catalyst.
- 30 8. Use claimed in claim 1 to 7 wherein said second
polyethylene polymer is an ethylene/hexene copolymer or
ethylene/butene/hexene terpolymer.
9. Use as claimed in claim 1 to 8 wherein the density
35 of the second polyethylene polymer is less than 935
kg/m³.

- 12 -

10. A polymer composition comprising:

A) 0.5 to 5% wt of a polyethylene homopolymer having a density of at least 950 kg/m³; and

5

B) at least 95% wt of a polyethylene co- or terpolymer with at least one C₃₋₁₀ α -olefin, said polymer having a density of less than 940 kg/m³.

10 11. A film comprising a polymer as claimed in claim 10.

12. A film as claimed in claim 11 having a Haze (ASTM D 1003) of less than 40% and a gloss (ASTM D 523-66T) of at least 35.

15